


AR 0/4-650

Product : Expanded Clay

Client : Quality Control Argex
 Tel.: +32/32.50.15.08
 Fax: +32/32.50.15.28

Lab	Quality Control Argex Tel.: 0032/32.50.15.08 Fax.: 0032/32.50.15.28
Aggregate Size	0/4 mm
Certifications	CE: EN 13055-1, EN 13055-2 : ISO 9001:2000
CE: EN 13055-1, EN 13055-2	Lightweight aggregates: -Part 1: Lightweight aggregates for concrete, mortar and grout -Part 2: Lightweight aggregates for bituminous mixtures and surface treatments and for unbound and bound applications

TESTS	Minimum	Average	Maximum	Declared	Standard
Particle Shape		Round			EN 13055-1
Crushing Resistance (T-2x30")		Not Relevant			EN 13055-1
Estimated Particle Density	967	1162 kg/m ³	1309	1138	
Loose Bulk Density	552	664 kg/m ³	748	650	EN 1097-3
Freezing & Thawing Resistance		3.3 %		4	EN 13055-1
Los Angeles + Micro Deval (4-6.3)		NPD*			EN 1097-1 & 2
Los-Angeles (4-6.3)		NPD*			EN 1097-2
Polished Stone Value		NPD*			EN 1097-8
Volume Stability		0.12 %			EN 13055-1
Water Content	0.0	3.6 %	30.0		EN 1097-5
Water Absorption (5')		Not Relevant			EN 1097-6
Water Absorption (30')		Not Relevant			EN 1097-6
Water Absorption (24h)		Not Relevant			EN 1097-6
Alkali Silica Reactivity		Not Relevant			EN 13055-1
Chemical Analysis Argex		100.00 %			
SiO ₂	55	59.50 %	65		
Mn ₂ O ₃	0.15	0.20 %	0.25		
K ₂ O	1.5	3.00 %	3.5		
TiO ₂	0.8	0.90 %	1		
MgO	1	1.50 %	2		
S	0.7	1.00 %	1.3		
Al ₂ O ₃	15	17.00 %	19		
Na ₂ O	0.3	0.50 %	0.7		
Fe ₂ O ₃	12	14.30 %	16		
P ₂ O ₅	0.05	0.10 %	0.15		
CaO	1	2.00 %	3		
Chloride		0.005 %		0.02	EN 1744-1
Cleanliness		OK			EN 1744-1
Emission Of Radioactivity		NPD*			EN 13055-1
Loss on Ignition		-0.18 %		5	EN 1744-1
Release Of Heavy Metals		NPD*			EN 13055-1
Release Of Other Dangerous Substances		NPD*			EN 13055-1
Release Of Polyaromatic Carbons		NPD*			EN 13055-1
Reaction To Fire		A1			EN 13501-1
Total Sulphur		0.323 %		0.8	EN 1744-1
Acid-Soluble Sulfate		0.054 %		0.8	EN 1744-1




AR 0/4-650

Product : Expanded Clay

Client : Quality Control Argex
 Tel.: +32/32.50.15.08
 Fax: +32/32.50.15.28

Lab	Quality Control Argex Tel.: 0032/32.50.15.08 Fax.: 0032/32.50.15.28
Aggregate Size	0/4 mm
Certifications	CE: EN 13055-1, EN 13055-2 : ISO 9001:2000
CE: EN 13055-1, EN 13055-2	Lightweight aggregates: -Part 1: Lightweight aggregates for concrete, mortar and grout -Part 2: Lightweight aggregates for bituminous mixtures and surface treatments and for unbound and bound applications

Grading (Standard EN 933-1)				
Mass				
Sieve (mm)	Minimum	% passing	Maximum	Declared
0.000	0.0	0.0	10.0	
0.063	1.0	4.1	15.0	
0.125	2.0	8.1	18.0	
0.250	5	12	25	
0.500	8	16	28	
1.000	15	24	35	
2.000	35	52	60	
3.150	68	86	93	
4.000	90	98	100	
5.000	95	100	100	



NPD* = No Performance Determined