

AG 1/5-390

Client : Quality Control Argex
 0032/32.50.15.15

lab	Quality Control Argex 0032/32.50.15.15
Aggregate Size	1/5 mm
Certifications	EN 13055 : NL BSB K73820 (1/01/2004)

Essential char. - performance	Minimum	Average	Maximum	Declared	Standard
Particle Shape		Crushed			EN 13055
Crushing Resistance (T-2x30")		NPD			EN 13055
Loose Bulk Density (+- 15% of declared value)	332	387 kg/m ³	449	390	EN 1097-3
Oven-Dried Particle Density (+- 15% of declared value)	663	779 kg/m ³	897	780	EXCA Guideline
Freezing & Thawing Resistance		2.3 %	3.3		EN 1367-7
Los Angeles + Micro Deval (4-6.3)		NPD			EN 1097-1 & 2
Los-Angeles (4-6.3)		NPD			EN 1097-2
Polished Stone Value		NPD			EN 1097-8
Volume Stability		0.22 %	0.50		EN 1367-8
Water Content (from silo)	0.0	2.3 %	15.0		EN 1097-5
Water Absorption 5'	32.70	36.09 %	40.54		EXCA Guideline
Alkali Silica Reactivity		NPD			EN 13055
Chloride		0.005 %	0.010		EN 1744-1
Cleanliness		Pass			EN 1744-1
Release Of Dangerous Substances		NPD			EN 13055
Reaction To Fire		Euroclass A1			EN 13501-1
Total Sulphur		0.13 %	0.55		EN 1744-1
Acid-Soluble Sulfate		0.209 %	0.500		EN 1744-1

Grading (EN 933-1)				
sieve (mm)	mini	% passing	maxi	Declared
0.000		0.0		
0.063		3.5		
0.125		5.5		
0.250		6.6		
0.500		7.4		
1.000	0.0	8.5	15.0	
2.000		17		
3.150		49		
4.000		74		
5.000	90	94	100	
6.300		99		

